



SEAMLESS VS WELDED PIPE THICKNESS

Type of Pipe	Grade	Schedule	Thickness (mm)	Thickness (inches)
Seamless	304/304L	5S	1.65	0.065
Seamless	304/304L	10S	3.05	0.12
Seamless	304/304L	40S	4.55	0.18
Seamless	304/304L	80S	7.95	0.312
Seamless	304/304L	160	12.7	0.5
Seamless	304/304L	XXS	15.9	0.625
Seamless	316/316L	5S	1.65	0.065
Seamless	316/316L	10S	3.05	0.12
Seamless	316/316L	40S	4.55	0.18
Seamless	316/316L	80S	7.95	0.312
Seamless	316/316L	160	12.7	0.5
Seamless	316/316L	XXS	15.9	0.625
Welded	304/304L	5S	1.65	0.065
Welded	304/304L	10S	3.05	0.12
Welded	304/304L	20	2.11	0.083
Welded	304/304L	30	2.77	0.109
Welded	304/304L	40S	4.55	0.18

Welded	304/304L	80S	7.95	0.312
Welded	304/304L	160	12.7	0.5
Welded	304/304L	XXS	15.9	0.625
Welded	316/316L	5S	1.65	0.065
Welded	316/316L	10S	3.05	0.12
Welded	316/316L	20	2.11	0.083
Welded	316/316L	30	2.77	0.109
Welded	316/316L	40S	4.55	0.18
Welded	316/316L	80S	7.95	0.312
Welded	316/316L	160	12.7	0.5
Welded	316/316L	XXS	15.9	0.625



SEAMLESS STAINLESS STEEL PIPES CHART

Grade	Schedule	Thickness (mm)	Thickness (inches)
304/304L	5S	1.65	0.065
304/304L	10S	3.05	0.120
304/304L	40S	4.55	0.180
304/304L	80S	7.95	0.312
304/304L	160	12.7	0.500
304/304L	XXS	15.9	0.625
316/316L	5S	1.65	0.065
316/316L	10S	3.05	0.120
316/316L	40S	4.55	0.180
316/316L	80S	7.95	0.312
316/316L	160	12.7	0.500
316/316L	XXS	15.9	0.625